



Mag. value. DIN IEC 60404-8-	Conditions	Min	Typ	Max	Unit
Remanence Br		430	450		mT
Coercivity HcB		215	239		kA/m
Coercivity HcJ		217	241		kA/m
Max. operating temperature				100	°C
Magnetic moment	inclusive of 5% tolerance	10,6	13,1		E-6 Vs*cm
Magnet Material		Hard Ferrit, Y35			
Direction of Magnetization		axial			

General data	Conditions	Min	Typ	Max	Unit
Total weight		3,8	4,2	4,7	g
Remark		material of float: PP, grey RAL 7037			
Remarks		All details according to manufacturers information			
Remarks		Magnet part number: 4001311093			