



Special Product Data	Conditions	Min	Typ	Max	Unit
Float weight				3,5	g
Material of float		PP dark grey, FDA approved			

Mag. value. DIN IEC 60404-8-	Conditions	Min	Typ	Max	Unit
Remanence Br		1.170	1.240		mT
Revers. temp. coeff. of Br			-0,11		%/K
Coercivity HcB		876	947		kA/m
Coercivity HcJ		1.353			kA/m
Revers. temp. coeff. of HcJ			-0,58		%/K
Density		7,5	7,6		g/cu cm
Max. operating temperature				120	°C
Magnetic flux			1.440		E-6 Vs
Magnetic moment	inclusive of 5% tolerance		22,4		E-6 Vs*cm
Magnet Material		NdFeB N35H, zinc plated			
Direction of Magnetization		axial			

General data	Conditions	Min	Typ	Max	Unit
Remarks		All details according to manufacturers information			